

PHYSICAL TESTING REPORT

LUCIDEON

insight creating advantage



0013

Tudor Roof Tile Company Limited
Denge Marsh Road
Lydd
Kent
TN29 9JH

FAO: Mr. Paul Lythgoe

Report of Tests on: Tudor Roof Tiles Handmade

Your Reference: Various Colours

Lucideon Reference: (143220)-14828

Date Reported: 23-Jul-2014

Order Number: PjL 270614

Date Logged: 03-Jul-2014

Date(s) of Test(s): 21-Jul-2014 to 21-Jul-2014

Determination of Flexural Strength

BS EN 538: 1994: Clay Roofing Tiles for Discontinuous Laying

| | Flexural Strength |
|------------|--------------------------|
| No. | kN |
| 1 | 0.80 |
| 2 | 1.08 |
| 3 | 1.34 |
| 4 | 1.13 |
| 5 | 1.18 |
| 6 | 1.24 |
| 7 | 1.12 |
| 8 | 1.32 |
| 9 | 1.37 |
| 10 | 1.06 |
| Mean | 1.16 |

Span: 178 mm

Does the sample comply with the BSEN1304: 2005 Clause 4.4.2? Yes

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

End of Test Report

Pass

Mr Simon Hall
Author

Page 1 of 1

This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455 Registered Office as above.

Lucideon Ltd
Queens Road, Penkull
Stoke-on-Trent
Staffordshire ST4 7LQ, UK
T +44 (0)1782 764428
enquiries@lucideon.com
www.lucideon.com
Reg. England 1960455