PHYSICAL TESTING REPORT



Tudor Roof Tile Company Limited

Denge Marsh Road Lydd Kent

TN29 9JH

FAO: Mr. Paul Lythgoe

Report of Tests on: TRT Handmade Various Colours

Your Reference: Plain&Peg

Lucideon Reference: (152667)-14945

Date Reported: 17-Jul-2015 Order Number: PjL010715

Date Logged: 03-Jul-2015 **Date(s) of Test(s):** 13-Jul-2015 **to** 14-Jul-2015

Determination of Impermeability of Clay Roofing Tiles

BSEN 539-1:2005 Method 2 & BSEN 1304:2005

	Time to First Drop (hr/min)	Impermeability Coefficient
No.		
1	20	0
2	20	0
3	20	0
4	20	0
5	20	0
6	20	0
7	20	0
8	20	0
9	20	0
10	20	0
Mean	20	0.0

The samples tested comply with Category 1

If 20 hours is indicated giving a coefficient of 0.00 this is equivalent to no drops of water noted throughout the 20 hour time period of the test. It is stated within clause 4.4.1 of BSEN 1304 that tiles classified as Category 1 shall have a mean impermeability coefficient after testing of 0.8 or less, and all individual results shall be 0.85 or less. Category 2 shall have a mean impermeability coefficient after testing of 0.925 or less, and all individual results shall be 0.95 or less. Tiles or fittings for roofs classified in Category 2 shall only be used with watertight roofing underfelt.

End of Test Report

